



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 849 296 A3

(12) EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
06.05.1999 Bulletin 1999/18

(51) Int. Cl.⁶: C08F 290/06, C08F 2/50,
C03C 25/02

(43) Date of publication A2:
24.06.1998 Bulletin 1998/26

(21) Application number: 97122119.7

(22) Date of filing: 16.12.1997

(84) Designated Contracting States:
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 20.12.1996 JP 341674/96

(71) Applicants:
• TAKEDA CHEMICAL INDUSTRIES, LTD.
Chuo-ku, Osaka 541 (JP)
• Shin-Etsu Chemical Co., Ltd.
Chiyoda-ku Tokyo 100 (JP)

(72) Inventors:
• Yamazaki, Kyuya,
c/o Takeda Chem. Ind. Ltd.
Yodogawa-ku, Osaka 532 (JP)
• Nishimura, Mitsuhiro,
c/o Takeda Chem. Ind. Ltd.
Yodogawa-ku, Osaka 532 (JP)

• Uemura, Takashi,
c/o Takeda Chem. Ind. Ltd.
Yodogawa-ku, Osaka 532 (JP)
• Yamamoto, Akira,
Shin-EtsuChem. Co. Ltd.
Usui-gun, Gunma 379-02 (JP)
• Kozakai, Shouhei,
Shin-EtsuChem. Co. Ltd.
Usui-gun, Gunma 379-02 (JP)
• Asano, Masatoshi,
Shin-EtsuChem. Co. Ltd.
Usui-gun, Gunma 379-02 (JP)

(74) Representative:
von Kreisler, Alek, Dipl.-Chem. et al
Patentanwälte,
von Kreisler-Selting-Werner,
Bahnhofsvorplatz 1 (Deichmannhaus)
50667 Köln (DE)

(54) A photocurable resin composition and a method for producing the same

(57) The invention provides a photocurable resin composition which inhibits the deactivation of a bisacylphosphine oxide-series photopolymerization initiator and is useful for coating optical fibers. The photocurable resin composition comprises (A) a polyurethane (meth)acrylate oligomer, (B) an ethylenically unsaturated compound, (C) a bisacylphosphine oxide-series photopolymerization initiator, and (D) a tertiary amine and no tin component. Incorporation of the component (D) inhibits the decomposition and deactivation of the component (C). The component (A) may contain an aliphatic C₁₄₋₄₀ polyol (hydrogenated dimerdol, 12-hydroxystearyl alcohol) as a polyol component. This resin composition is used for a primary coating of a glass fiber or an indirect coating of an optical fiber through the primary layer, the coating layer being cured by light irradiation to provide an optical fiber coated with the resin composition.

EP 0 849 296 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 12 2119

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	VALET A.: "Zur Wetterbeständigkeit UV-härtbarer Pulverklarlacke" FARBE + LACK, vol. 102, no. 1, 1996, pages 40-46, XP002094307 * page 41 *	1-3	C08F290/06 C08F2/50 C03C25/02
X	WO 96 29352 A (Dymax Corp) 26 September 1996 * page 17, line 14-34; examples; table 1 *	1-3	
X	EP 0 262 629 A (BASF AG) 6 April 1988 * claims; examples 1-3 *	1-3	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C03C C08F C08K C09J
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 22 February 1999	Examiner Friederich, P
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 97 12 2119

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-02-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9629352 A	26-09-1996	AU 4974196 A	08-10-1996
		CA 2215597 A	26-09-1996
		EP 0815146 A	07-01-1998
		JP 10510578 T	13-10-1998
		US 5672393 A	30-09-1997
		US 5677362 A	14-10-1997
EP 0262629 A	06-04-1988	DE 3633436 A	14-04-1988
		HK 11794 A	18-02-1994
		JP 1102455 A	20-04-1989
		JP 2604172 B	30-04-1997
		SG 136293 G	25-11-1994
		US 4868091 A	19-09-1989